


DEKO-DRAIN



Hard, elastic joint



Resistant to frost, UV, and salt



Weed-free



Highly permeable



For pedestrian traffic

Ideal paving system for drainage fields in areas with pedestrian traffic, where a highly permeable and decorative drainage solution is desired - weed-free.



LITHOMEX

- binds every stone together

Technical data

2-component coating system

Strength: 15 MPa
Density: 1.56 g/cm³
Grain size:
5/8 to 11/16 mm

Applications

Drainage fields in areas with pedestrian traffic, including around trees, as decorative spaces, along house walls, and on walkways and path systems.

Joint depth

30-75 mm

Functionality

Hardens to form a decorative, weed-free, and highly permeable drainage solution. Resistant to suction/sweeping machines.

Application

The application of Deko-Drain should take place in dry weather and between 5°C and 25°C. Pay attention to ambient, ground, and material temperatures.

Shelf life

Deko-Drain binder should be stored dry, away from direct sunlight and frost, for up to 12 months. Aggregates should be stored dry and have unlimited shelf life.

Colours



Red



Black



Grey

Colours



Als



Lolland



Fur

Hardening

3-4 days depending on temperature.
+10°C halves the curing time.
-10°C doubles the curing time.

Consumption guide for a thickness of 30 mm

Area

1.5 m²

Consumption per square meter

52 kg.

Consumption

75 kg. (3 x 25 kg)

How-to guide

BEFORE APPLICATION



Always carry out paving and substrate according to applicable regulations regarding expected usage.

Ensure that the sub-base of the area is permeable to water and properly constructed to prevent settlement damage to the surface.

Put 75 kg (3 x 25 kg) of aggregates into a forced mixer and start the machine. Afterward, add Deko-Drain components A & B simultaneously and let the machine run until the stone mixture is uniform, approximately 8 minutes. Note! Do not add water. Containers must be completely empty, as the mixing ratio is tailored to the size of the containers.

Remember protective equipment
- read the product's safety data sheet.



AT THE TIME OF APPLICATION



Pour the finished stone mixture onto the desired area and spread it evenly with a shovel or scraper.

Finely rake until the surface is smooth and even. In some places, it may be advantageous to compact with a light vibrating plate.

The paving surface should then have a minimum thickness of 30 mm.



ATTENTION! Clean the forced action mixer thoroughly with water. Clean shoes (soles are most important) and tools regularly with a dry broom.

How-to guide

AFTER APPLICATION



The grouted area, depending on temperature, can be walked on after approximately 24 hours and is fully cured after 3-4 days (in dry weather and around 20°C).


The area must not be exposed to water or frost during application and curing.

If coverings are used, they should allow for air circulation.

The transparent binder has a color-enhancing effect on the stones after application, which diminishes over time.



How Deko-Drain works



LITHOMEX

- binds every stone together

Please contact us for
counselling during
our opening hours



Lervejldal 14D • Addit • DK-8740 Brædstrup
Phone: +45 8622 1122 • info@lithomex.com • VAT no.: 37 39 48 74
www.lithomex.com